



# F9W-Water based

## PRODUCT DATA SHEET

### Fluorescent Powder for Wet Method Magnetic Particle Inspection

#### **DESCRIPTION**

ZChек F9W is a Green Colored water based Magnetic Particle Powder designed to be fluorescing Bright Green under UV Light. ZChек F9W consists of high sensitivity particles for detection of very fine discontinuities in Ferromagnetic materials. Using the state-of-the-art encapsulation technology, ZChек F9W is manufactured to exhibit excellent properties (High permeability, low retentivity, high mobility and optimum particle distribution) required for high sensitive fluorescent MPI process. Special additives in F9W provide excellent particle mobility in water medium and avoid flash rusting of parts.

#### **CONFORMANCE / SPECIFICATION COMPLIANCE**

- ASME B &PV Code, Sec V
- AMS 3044
- ASTM E 1444
- ASTM E 709
- EN ISO 9934-2

#### **APPLICATIONS**

ZChек F9W is designed to detect medium to fine surface and slightly subsurface discontinuities like inclusions, seams, shrink cracks, tears, laps, flakes, welding defects, grinding cracks, quenching cracks, and fatigue cracks in raw forgings, castings( during preliminary stage ), auto components(machining cracks, grinding cracks, heat treatment cracks), fabrication, steel making (billets and bars), surface transportation, oil and gas and all applications which involve further processing like machining and oiling.

## **TYPICAL PROPERTIES**

|                            |                           |
|----------------------------|---------------------------|
| Color Under White Light    | Green                     |
| Color Under Black Light    | Bright Green Fluorescence |
| Mean Particle Size         | 9- 14 Microns             |
| Particle Size Range        | 1-20 Microns              |
| Sensitivity                | 7 ( Ketos Ring )          |
| Max. Operating Temperature | 49°C Maximum              |
| Settling volume            | 0.05-0.15 ml              |

## **DIRECTIONS FOR USE**

- Use F9W at 10.75 – 11 grams per litre. Run the pump for 15 minutes before testing.
- Check the concentration before use at least once each day using centrifuge tube.
- Parts should be clean and dry prior to testing.
- The bath must be under continuous agitation
- Using the wet continuous method, the bath is applied to all surfaces of the part. The instant the bath stream is removed from the part the magnetizing current is applied.

## **PACK SIZES**

1 kg X 4 Nos-1 Carton box

## **HEALTH & SAFETY**

Information on Health & Safety is made available through Material Safety data sheets and the same can be reviewed through the company's website [www.zchem.in](http://www.zchem.in)

## **STORAGE & SHELF LIFE**

Packed Powders have a shelf life of 5 years if unopened and stored as per ZChem Recommendations

Manufactured By:

## **ZChem Specialities Pvt Ltd**

Sy.No. 11/2/6, Puradapalya Village, Tavarekere Hobli, Bangalore – 562130, India

Phone +917349177755 & +917349277755 Email – [info@zchem.in](mailto:info@zchem.in) , Website – [www.zchem.in](http://www.zchem.in)

Disclaimer: We have taken best care to ensure that the information provided in this data sheet is accurate. Our product is guaranteed to conform to the specifications provided. We make no other warranty; hence the liability is limited to replacement of product only.

Doc. No.PDS/002/B-Oct-21

